

ZINCOMAR



RIVESTIMENTO SPECIALE PER SUPERFICI ZINCATE

Di aspetto semilucido, questo smalto viene utilizzato come manouica per la protezione di superfici zincate, di alluminio, di cemento, di materiali plastici rigidi esenti da precedenti pitture o incrostazioni. È formulato con pigmenti selezionati che assicurano notevole resistenza all'invecchiamento e perfetta aderenza al supporto, evitando lo sfogliamento della pittura.

CAMPI D'IMPIEGO

Zincomar è indicato per la protezione di superfici zincate esposte agli agenti atmosferici (canali di scarico, grondaie e pluviali, alluminio) sulle quali può essere applicato come manouica e con potere consolidante su manufatti in cemento-amianto, tutti esenti da precedenti pitture o da ruggine.

APPLICAZIONE

L'applicazione va eseguita su supporti zincati stagionati, preventivamente puliti e sgrassati con diluente per lavaggio. Per l'applicazione a pennello, diluire il prodotto con il 5-10% di diluente speciale 082.000; per l'applicazione a spruzzo, diluire con il 15-20% di diluente.

Il prodotto pronto all'uso contiene 500 g/l max di COV, appartiene alla cat. A/i "Pitture monocomponenti per alte prestazioni" il cui valore massimo UE in COV è 500 g/l.

SPECIAL COATING FOR GALVANIZED SURFACES

This semi-glossy enamel is applied as a single coat for the protection of galvanized, aluminium or cement surfaces and rigid plastic materials that have been stripped of previous layers of paint or deposits. It is formulated with selected pigments that ensure it has a considerable resistance to ageing and that it adheres perfectly to the surface, which prevents the paint from peeling.

FIELDS OF USE

Zincomar is suitable for protecting galvanized surfaces that are exposed to weathering (drainage channels, gutters and downspouts, aluminium) on which it can be applied as a single coat; it has a consolidating action on asbestos-cement products, all of which must be free from traces of paint or rust.

APPLICATION


The galvanized metal surfaces must be free of rust, sufficiently hard and degreased with a thinner for washing. For brush application, dilute 5-10% with the special thinner 082.000; while for spray application, dilute 15-20% with thinner 082.000.

The ready-to-use product contains 500 g/l VOC and belongs to category A/i "High performance one component paints", the EU limit value is 500 g/l.

DATI TECNICI | TECHNICAL DATA

DILUENTE THINNER	speciale 082.000 5-10% pennello/brush - 15-20% spruzzo/spray
APPLICAZIONE APPLICATION	pennello / spruzzo brush / spray
SOVRAPPLICAZIONE RECOAT TIME	manouica single coat
ESSICAZIONE DRYING TIME	2 h in superficie - 12 h in profondità surface dry 2 h - thoroughly dry 12 h
RESA INDICATIVA APPROXIMATE COVERAGE	8 m ² /l
FINITURA FINISH	semilucido semigloss
TINTE DISPONIBILI AVAILABLE COLOURS	<div style="display: flex; gap: 5px;"> <div style="background-color: black; color: white; padding: 2px;">900</div> <div style="background-color: black; color: white; padding: 2px;">808</div> <div style="background-color: black; color: white; padding: 2px;">425</div> <div style="background-color: white; color: black; padding: 2px;">100</div> <div style="background-color: black; color: white; padding: 2px;">327</div> <div style="background-color: black; color: white; padding: 2px;">629</div> </div>

FORMATI DISPONIBILI | AVAILABLE FORMATS



I dati, le informazioni e i suggerimenti contenuti nella presente scheda, si basano su prove del Laboratorio Tecnico, esse non possono tuttavia costituire garanzia od obbligazione alcuna da parte di IPV srl. È cura dell'utilizzatore controllare le condizioni di applicazione, essendo soggette a molteplici variabili.

The data, information and suggestions contained in this data sheet are based on tests carried out by the Technical Laboratory; however, they do not imply any guarantee or obligation on the part of IPV srl. It is the responsibility of the user to check the conditions of application, as there are multiple variables involved.